TECH-DRY BUILDING PROTECTION SYSTEMS PTY. LTD.

ACN 005 307 684 ABN 62 922 836 289

177-179 Coventry Street,

South Melbourne, Victoria 3205, Australia Telephone: 61 3 9699 8202 (all hours)

Facsimile: 61 3 9696 3362 Website: www.techdry.com.au E-mail: info@techdry.com.au



PRODUCT INFORMATION

POWDERSIL 60 Page 1 of 1

Updated: 01/01/2018 Manufacturer's code: RPPOWDERSIL60

Product Name: POWDERSIL 60

Description: POWDERSIL 60 is highly effective silicone-based water repellent admixture designed

as a free-flowing powder form for cementitious products.

Recommended Uses: As free-flowing powder, POWDERSIL 60 can be blended with dry ingredients of

> cementitious material to provide hydrophobic property to the cementitious products. It is particularly useful in grouts, joint fillers, mortar and façade rendering applications.

Some of the important features of POWDERSIL 60 include:

Reduces water absorption and efflorescence of cementitious product.

Remains permanently bonded in the entire substrate and cannot be washed out.

Does not leave any oily residue on the substrate.

Easy to use in any existing production processes.

The degree of water repellency can be varied by changing the rate of addition.

Easy mixing with other cementitious ingredients and dispersing in water.

Use Instructions: It is important that the applicator should perform trials before application.

1. Dosage

The dosage of POWDERSIL 60 depends on the specific mix design and the level of water repellency that is required. The use level is between 0.1% to 2% based on the total dry weight of the finished product.

2. Addition

POWDERSIL 60 can be added at any time during production of cementitious material. However, end user should carry out test to find the best suitable way of mixing

POWDERSIL 60 into the product. Ensure that the product is evenly dispersed.

Typical Data: Appearance: White free-flowing powder with slight odour

> Particle size distribution: 100% @ <500micron

Mean particle size: 300 micron Bulk density: 600 g/l

As condition varies, it is recommended that a pilot trial should be carried out prior to **Important Note:**

using POWDERSIL 60 to determine the suitability of this product for the purpose.

Handling & Storage: POWDERSIL 60 is a non-hazardous material. However, good industrial hygiene

> procedures should be followed when handling. The product should be stored in closed containers in a cool dry place away from any fire sources. The product has a shelf life

of 12 months in a sealed container stored at a temperature below 25°C.

Packaging: POWDERSIL 60 is available in 10kg bags. Other type of package may be available on

request.

Disclaimer:

The information given in this data sheet is based on many years of experience and is correct to the best of our knowledge. As the storage, handling and application of this material are beyond our control; we can only be responsible for the quality of our product at the time of dispatch. We reserve the right to alter certain product parameters within the spectrum of properties in order to keep abreast of technical advances. It is the responsibility of the end user to determine the suitability of this material for any particular application.